

GENERAL COMMENTS

DEPOSIT CHARACTERISTICS

Deposit Number	Material Description	Reserves (1000 m ³)		Additional Comments	Texture (%)			Overburden Thickness (m)	Deposit Thickness (m)	Deposit Area (ha)	Deposit Genesis	Additional Comments
		Gravel	Sand		Gravel	Sand	Fines					
1	Dirty gravelly sand	242	366	Water table at 3.0 m; loose structure. Abandoned pit.	38	56	6	0.5	3.0	21	Outwash	Precambrian rocks and quartzites are common; some coal fragments, petrified wood and ironstones; mainly coarse to medium sand and fine gravel.
2	Dirty sandy gravel	261	166	Water table at 2.5 m; poor quality; loose structure. Abandoned pit.	55	35	10	0.2	2.5	19.0	Outwash	Precambrian rocks and quartzites common; massive; principally fine gravel.
3	Dirty gravelly sand	234	5070	Water table unknown, probably >4.0 m	30	65	5	0.5	3.0	26	Outwash terrace	Mainly Precambrian rocks and quartzites; some ironstones; medium sand; limited information sources.
4	Dirty sandy gravel	645	322	Water table at 2.0 m; High clay content; poor quality. Abandoned pit.	60	30	10	0.3	2.5	43	Outwash terrace	Precambrian rocks and quartzites common; soft weathered materials present; coal fragments; massive.
5	Dirty gravelly sand	202	412	Water table unknown; poor quality.	35	55	10	0.3	1.5	50	Outwash terrace	Similar to Deposit #4, except sandy.
6	Sand	19 594	-	Deposit contains fine grained sand; approx. 40% covered by dunes.	97	3	-	-	4.0	1250	Eolian	High water condition between interdune zone during early spring season
7	Sand	2747	-	Deposit contains fine grained sand; approx. 40% covered by dunes.	97	3	-	-	3.0	236	Eolian	Marsh in interdune areas.

Deposit Number — Granular deposits shown on this map may have commercial possibilities. That assumption followed from two criteria used in the mapping process: study of the area considered only granular deposits greater than one metre thick, and covering an area more than one hectare; and it only considered deposits where the mineral aggregate thickness was greater than the overburden thickness. Although the scale of mapping did not permit investigation of all small deposits, many small deposits containing existing pits are indicated.

Material Description — Sand and gravel has a variety of applications, such as concrete for construction, asphalt concrete, subbase and base course aggregate for roads, gravel and sand for road surfaces, and pit run for fill. Gradation, rock hardness, and binding characteristics, are some of the specific qualities that are considered in aggregate towards determining its end use. This map indicates these, and other, geological qualities of the sand and gravel within each deposit, but does not indicate their potential uses. The terms used in the table are defined in the figure below.

Reserves — The method of calculating in cubic metres the aggregate reserves of deposits took four basic steps. First, the area, in hectares, of each deposit was determined using aerial photographs. Second, geological interpretation, sometimes supported by subsurface information, was assumed in determining the geometry of each deposit, to estimate an overall, average deposit thickness in metres. Third, geological study and limited sample analysis determined the texture (gradation) of sediments in the deposit; and an overall average percentage of gravel and sand. Finally, the volume was calculated as follows: reserve gravel (m³) = area (ha) × thickness (m) × 10,000 × % gravel; the same formula was used for sand.


Texture — The texture of the sediment refers to the percentage of particles of various sizes. For mineral aggregate, the most important fractions are the gravel and sand. The actual dimensions of the clasts and particles in these fractions are given in the figure. The values given for a particular deposit were determined from a field estimate, or from laboratory analysis, of one or more samples from that deposit. Where more than one sample is taken the tabulated number is the mean value.

Wear — The resistance of gravel-size clasts to wear or abrasion can be measured in a laboratory test (ASTM C131, Los Angeles Abrasion Testing). The amount of material that breaks down into smaller sizes is measured and related to the original sample weight in terms of percent wear. The higher the percentage wear the more susceptible the gravel is to breakdown under stress. Gravel with a percentage wear of less than 40 is considered very resistant.

Overburden Thickness — The thickness of non-economic material, or overburden, covering a deposit, sometimes is a limiting factor in the exploitation of an aggregate deposit. The tabulated values given are approximate overburden thicknesses as determined from geological investigations and subsurface testing.


Deposit Area — Deposits in this study were delineated by interpretation of aerial photographs and the contacts should be considered approximate. Information is precise only where test holes, or geological sections, are indicated.

Deposit Genesis — The genesis, or formation, of deposits is vital to the understanding of the gradational nature, extent and geometry of the deposit. This understanding forms the basis for extrapolation from a limited number of known points (test holes, pits, sections) and permits an overall assessment of the deposit.



Map Legend

- 3 Deposit number
- Assumed boundary
- Active or inactive pit
- Alberta Geological Survey test hole
- Sand or gravel exposure
- Buried sand or Gravel deposit



Produced by the SURVEYS AND MAPPING BRANCH, DEPARTMENT OF ENERGY, MINES AND RESOURCES, based on aerial photographs taken in 1976. Crown copyright 1977. Printed in Canada.

Cartes produites par le Service des levés et de la cartographie, Ministère de l'Énergie, des Mines et des Ressources, à partir de photographies aériennes prises en 1976. Droits de copyright 1977. Imprimé au Canada.

Cartes produites par le Service des levés et de la cartographie, Ministère de l'Énergie, des Mines et des Ressources, Ottawa, en vertu de la Loi sur l'accès à l'information.

Cartes produites par le Service des levés et de la cartographie, Ministère de l'Énergie, des Mines et des Ressources, Ottawa, en vertu de la Loi sur l'accès à l'information.

Cartes produites par le Service des levés et de la cartographie, Ministère de l'Énergie, des Mines et des Ressources, Ottawa, en vertu de la Loi sur l'accès à l'information.

CHAIN LAKES ALBERTA

WEST OF FOURTH MERIDIAN - OUEST DU QUATRIÈME MÉRIDIEN

Scale 1:50,000 Échelle

CONTOUR INTERVAL: 25 FEET

ÉCHARTONNEMENT DES COURBES: 25 PIEDS

AGGREGATE RESOURCES CHAIN LAKES 83A/11

This is a sand and gravel resource map prepared by the Alberta Geological Survey as part of a series at a scale of 1:50,000. The series represents an ongoing aggregate inventory of Alberta which provides data for general land-use planning, land management or aggregate exploration. Please note that the delineation of deposits and calculation of reserves are approximations only.

Source
Geology and compilation by P. Sham, 1980. Additional information from M.E. Holter, 1979 and A. MacS. Sosker, 1960